

Amendments to the Specification

Pursuant to 37 CFR 1.121(b)(iii), please substitute the following for the first paragraph on page 15 of the specification.

Polymer	Example	
	1	2
Appear™ 3000-B	10	
AryLite™ A100		10
Ruthenium dioxide powder	21.6	21.6
Bismuth ruthenate powder	15.7	15.7
Silver powder	5.0	5.0
Alumina	4.5	4.5
Dowanol® PPH	56	
BLO		56

Example	Tg	% H ₂ O	% Resistance Change			85°C/85% RH (500 hrs)
	(°C)	Absorption	Solder Float (3 x 10 sec)	<u>230°C</u>	<u>260°C</u> <u>288°C</u>	
1	330	0.03	-0.9	28.4	205	+1.8
2	325	0.4	-1.5	32.9	--	-3.4